



Precision Cable Ties

Technical Information

Material	Grade	Width (mm)	Length (mm)	Min. Break Strain (kgf)	Min. Bundle Diameter (mm)	Max. Bundle Diameter (mm)
Nylon	Polyamide 6.6	2.50	100	8.16	3.00	20.50
Nylon	Polyamide 6.6	2.50	150	8.16	3.00	36.50
Nylon	Polyamide 6.6	2.50	200	8.16	3.00	52.50
Nylon	Polyamide 6.6	3.60	150	18.35	3.50	36.00
Nylon	Polyamide 6.6	4.80	200	23.45	3.50	49.50
Nylon	Polyamide 6.6	4.80	250	23.45	3.50	65.00
Nylon	Polyamide 6.6	4.80	280	23.45	3.50	74.80
Nylon	Polyamide 6.6	4.80	300	23.45	3.50	81.00
Nylon	Polyamide 6.6	4.80	350	23.45	3.50	97.00
Nylon	Polyamide 6.6	4.80	370	23.45	3.50	103.50
Nylon	Polyamide 6.6	4.80	400	23.45	3.50	113.00
Nylon	Polyamide 6.6	4.80	450	23.45	3.50	129.00
Nylon	Polyamide 6.6	4.80	920	23.45	3.50	278.00
Nylon	Polyamide 6.6	7.60	300	55.06	8.50	82.80
Nylon	Polyamide 6.6	7.60	370	55.06	8.50	103.50
Nylon	Polyamide 6.6	7.60	450	55.06	8.50	130.50
Nylon	Polyamide 6.6	7.60	500	55.06	8.50	146.50
Nylon	Polyamide 6.6	7.60	550	55.06	8.50	162.50
Nylon	Polyamide 6.6	8.80	710	81.58	8.50	195.00
Nylon	Polyamide 6.6	8.80	810	81.58	8.50	245.00
Nylon	Polyamide 6.6	9.00	920	81.58	8.50	280.00
Nylon	Polyamide 6.6	9.00	1,020	81.58	8.50	295.00
Nylon	Polyamide 6.6	9.00	1,168	81.58	8.50	340.00
Nylon	Polyamide 6.6	9.00	1,220	81.58	8.50	375.50
Nylon	Polyamide 6.6	9.00	1,530	81.58	8.50	450.00
Stainless Steel	316	4.60	360	90.75	15.00	112.80
Stainless Steel	316	4.60	520	90.75	15.00	163.80
Stainless Steel	316	4.60	840	90.75	15.00	265.70
Stainless Steel	316	4.60	1,020	90.75	15.00	323.00

Storage and Handling

To ensure that cable ties remain effective, it is recommended that they are stored correctly in accordance with the manufacturer's directions.

Always store your cable ties in the supplied and sealed polyethylene bag, keep out of direct sunlight and away from any other heat sources. The optimum storage temperature is between 15 °C and 25 °C with a relative humidity of 50%.

Precision Cable Ties

25 Miowera Road

Villawood NSW 2163

(02) 9780 9000

sales@precisioncableties.com.au